

DESCRIPTION

DESCRIPTION			EXTREME
Surface			X PUR scuff-resistant surface
Backing			Combined closed cell foam system
Thickness	mm	EN ISO 24346	8,0
Top layer	mm	EN ISO 24340	1,2
Weight	g/m ²	EN ISO 23997	4250
Width	m	EN ISO 24341	2
Standard roll length	kg/m ²	EN ISO 24341	15 ± 10%

CLASSIFICATION

Product specification		EN 14904	Vinyl indoor sports floor (category P2)
Impact sound insulation	dB	EN ISO 717-2	21
Thermal resistance	m ² K/W	EN 685	0,08
Reaction to fire	-	EN 13501	C _{fl} -s1


















SPORT PROPERTIES



Friction	-	EN 13036-4	80-110
Shock absorption	%	EN 14808	≥ 35 (P2)
Vertical deformation	mm	EN 14809	1
Ball rebound	%	EN 12235	98
Specular gloss	%	EN 2813	< 30

TECHNICAL CHARACTERISTICS

Dimensional stability	%	EN ISO 23999	± 0,2
Indentation resistance	mm	EN 1516	< 0,5
Resistance to rolling load	N	EN 1569	1500
Colour fastness	-	EN 13036-4	6
Chemical resistance	-	EN ISO 26987	- no change
Abrasion resistance	mg/1000 cycles	EN ISO 5470-1	< 250

OTHERS

						
1360	1596	2089	3096	3338	4081	4289
						
6115	6170	6470	7143	7483	7539	
						
1171-371	2000-378	2209-371	2519-371			



GRABOPLAST LTD.

H-9023 Győr, Fehérvári út. 16/b. Telefon: (+36) 96 506-100
 instagram.com/graboplast | facebook.com/graboplast
 www.grabo1905.com

